

USP™ ENERGYKOTE ACRYLIC ROOF COATING

Product Data Sheet

PRODUCT INFORMATION: USP™ ENERGYKOTE is a bright white, single component, low viscosity, high-body, 67% solids emulsion polymer, based on pure acrylic polymer based resins for spray, brush, or roller application. USP™ ENERGYKOTE is designed to provide excellent waterproofing capabilities. Its bright white finish helps reduce surface temperatures thereby minimizing thermal expansion and contraction while providing long-lasting and preventative solutions for the renewal and maintenance of many roof types.

RECOMMENDED USES:

- As a general-purpose roof coating.
- As a restoration coating over metal roofs, and properly prepared EPDM.
- As a base coat/top coat over polyurethane foam, concrete, masonry, primed metal, primed wood, and primed asphalt.
- As a base coat/top coat over smooth BUR, modified bitumen and granular cap sheets in conjunction with USP™ BleedBlock.
- Significantly lowers roof surface temperatures, which can help reduce energy cooling bills.
- Contact U.S. Ply, Inc. for specific uses.

PRODUCT CHARACTERISTICS:

Finish: Satin
Color: Bright White
Viscosity: 110 ± 5KU (nominal)
Specific Gravity: 1.41
Weight: 11.7 lbs./gal.
VOC: <50 grams/liter
Recommended Spread Rate: 67 sq. ft./gal. per coat (nominal)



Drying Schedule: At 75 sq. ft. / gal

	<u>50F</u>	<u>70F</u>	<u>110F</u>
To Touch	4 hrs.	2 hr.	45 min.
To Recoat	1 day	6 hrs.	4 hrs.
To Cure	30 days	20 days	10 days

Note: Drying time is temperature, humidity, and film thickness dependent.

SHIPPING INFORMATION:

<u>Container Size</u>	<u>Gross Weight</u>	<u>Class</u>
5 Gal.	60 Lbs.	55
55 Gal.	660 Lbs.	55

D.O.T. Classification: Roof Coating, Not Regulated

HMIS:	Health	1
	Flammability	0
	Reactivity	0
	Protection	X

PERFORMANCE CHARACTERISTICS

Physical Properties:

PHYSICAL PROPERTY	TYPICAL VALUE	TEST METHOD
Solids Content By Weight:	67% ± 2%	(ASTM D-1644)
Solids Content By Volume:	52% ± 2%	(ASTM D-2697)
Tensile Strength:	150 psi ± 25	(ASTM D-2370)
Elongation:	300% ± 50%	(ASTM D-2370)
Initial Solar Reflectance:	.85	
Reflectivity (White):	82%	(ASTM C-1549)
Emissivity (White):	.84	(ASTM C-1371)

Shelf Life: (Unopened) – 12 months from date of shipment
Flammability: Non-Flammable
DO NOT FREEZE

PROPERTY	TEST PROCEDURE	RESULT
Accelerated Weathering UV Resistance	ASTM G-53	No degradation after 1,000 hours
Permeability	ASTM E-1653	5.0 perms at 20 mils
Low/High Temperature	ASTM D-822	Films retained their ability to be flexed 180° without cracking at temperatures from -15°F to 130°F with no age hardening or slump

All values given are approximate and are subject to change without notice. There is no implied or express warranty given through these values or statements, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by "in-house" and independent "third party" evaluation for the purpose of classification and/or approval. Acceptance, purchase and selection of these products are the sole responsibility of the buyer or buyer's representative. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY U.S. PLY, INC. EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

USP™ ENERGYKOTE ACRYLIC ROOF COATING

Product Data Sheet

APPLICATION PROCEDURES

USP™ ENERGYKOTE

TEMPERATURE

Air and Surface: 50°F Minimum/140°F Maximum
Material: 50°F Minimum/100°F Maximum

RELATIVE HUMIDITY

Can be applied at relative humidity up to 90%

DO NOT APPLY WHEN THE TEMPERATURE CAN FALL TO WITHIN 5°F OF THE DEW POINT WITHIN 6 HOURS.

This product cures by water evaporation only. It is very important that this product is not used when weather conditions are below 50°F or when there is a chance that the temperature could fall below 32°F within a 24 hour period after application. Do not apply this product if rain or dew is likely to occur before drying of product. Late afternoon application is not recommended if high humidity conditions exist, which could cause high moisture concentration of the surface overnight.

BRUSH: No reduction necessary. Use nylon/polyester brush. Do not over-brush as material may start to pull.

ROLLER: No reduction necessary. Use 1/2" to 1-1/2" nap synthetic rollers. Keep a wet edge to avoid ripping which may change appearance. If ripping is a problem, extend lap time to after materials have skinned. Avoid rapid rolling which causes bubbling.

AIRLESS SPRAY-VOLUME:

Output: 2 – 3 gal. per min.
Pressure: 3,000 – 4,000 psi
Spray Gun: Graco – Contractor rated for pressure
Tip: .021 -.025 reversible
Extension: 12" – 18" gun extension recommended

SPECIAL CONDITIONS

Mildew

- Must be removed by power washing and broom scrubbing with a solution of household bleach or liquid detergent and water. Rinse clean and dry.

Ponding Water:

- **U.S. Ply, Inc.'s Warranties do not cover damage due to ponding water.**
- Water based coatings should not be applied on roofs collecting ponding water. The National Roofing Contractors Association considers ponding water on any roof unacceptable. (See the NRCA Roofing and Waterproofing Manual).
- Do not use without a vapor barrier in cryogenic tank or cold storage roofing applications.

Surface Preparation: All surfaces to be coated must be clean, dry, and paintable. It may be necessary to power wash and/or prime to enhance adhesion. See application specification for more details.

Mixing Procedures: No thinning or reducing is necessary. Product may separate after shipping and storage, though it may still look mixed. When mixing becomes necessary we recommend the use of a 3/4 horsepower or larger electric or air operated mixer with a blade capable of uniformly mixing the entire container. When product is in 5-gallon pails, use a 3" minimum diameter mixing blade. When product is in drums, use a 6" minimum diameter mixing blade.

Application Equipment: This product may be sprayed, brushed, or rolled. When using spray equipment, it is important that the following criteria are met: When using a spray pump, a 30:1 or 45:1 fluid to air ratio capable of delivering 2 1/2 gallons or more per minute continuous is needed, as well as a filter screen of 30 mesh or larger. If a fluid spray hose is used, it should be high pressure with designed working pressure to handle maximum pressure delivered by the spray pump. Inside lining or tube should be of such a material so it is unaffected by the coating and any solvents used for clean up. Additionally, the following criteria should be used for hoses: 3/8" minimum I.D. up to 75 feet; 1/2" minimum I.D. up to 200 feet; and 3/4" minimum I.D. over 200 feet. Material temperature should be 70°F or higher. The larger I.D. sections of hose should be used from the pump out in all circumstances with additional hose size reductions as necessary.

If a gun hose whip is used, high pressure with adequate W.P.S.I. 3/8" I.D. X 6 feet with an appropriate lining or tube is recommended. When using a spray gun, we recommend the Graco Hydra Max or equivalent. High-pressure gun swivels are available and can reduce operator fatigue. Any spray tip should be a reversible self-cleaning type with an orifice size of .021 to .025 with a fan angle of 40 to 50 degrees. Always use components rated for pump pressures.

Cleanup Instructions: Clean up spills and spatters immediately with water. After cleaning, flush spray equipment with water followed by propylene glycol to prevent unit from rusting.

SAFETY PRECAUTIONS: Refer to the MSDS sheet before use. For Chemical emergencies, spills, leaks, exposure, or accidents CALL: CHEMTREC DAY/NIGHT 1-800-424-9300.

U.S. PLY, INC.

A DANNY ADAIR COMPANY

Corporate Headquarters

P.O. Box 11740, Fort Worth, Texas 76110
TOLL-FREE: 866-PUSH-PLY (866) 787-4759
Local: (817) 413-0103 • Fax: (817) 413-8221

Website: www.usply.com • Email: energykote@usply.com

All values given are approximate and are subject to change without notice. There is no implied or express warranty given through these values or statements, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by "in-house" and independent "third party" evaluation for the purpose of classification and/or approval. Acceptance, purchase and selection of these products are the sole responsibility of the buyer or buyer's representative. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY U.S. PLY, INC. EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.